

Interzone 954

Modified Epoxy



Product Description

A two component, low VOC, high solids, modified epoxy barrier coat designed to give long term protection in a single coat application. Will continue to cure when immersed in water and has excellent cathodic disbondment resistance.

Intended Uses

Primarily designed for use in offshore splashzone maintenance, where its continued cure under immersed conditions make it ideal for coping with tidal movements and surges. May be applied to reoxidised and slightly damp surfaces. Interzone 954 has also found extensive use in a number of other corrosive environments including pulp and paper plants, chemical plants, jetties and sluice gates.

As part of a non-slip deck system in conjunction with appropriate aggregate.

Practical Information for Interzone 954

Colour	Range available via the Chromscan system.
Gloss Level	Gloss
Volume Solids	85% ± 3% (depends on colour)
Typical Thickness	350-500 microns (14-20 mils) dry equivalent to 412-588 microns (16.5-23.5 mils) wet
Theoretical Coverage	1.70 m ² /litre at 500 microns d.f.t and stated volume solids 68 sq.ft/US gallon at 20 mils d.f.t and stated volume solids
Practical Coverage	Allow appropriate loss factors
Method of Application	Airless spray, Air spray, Brush, Roller
Drying Time	

Temperature	Touch Dry	Hard Dry	Overcoating Interval with recommended topcoats	
			<i>Minimum</i>	<i>Maximum</i>
10°C (50°F)	14 hours	24 hours	24 hours	14 days
15°C (59°F)	10 hours	18 hours	18 hours	10 days
25°C (77°F)	4 hours	8 hours	8 hours	7 days
40°C (104°F)	90 minutes	3 hours	3 hours	5 days

Regulatory Data

Flash Point	Base (Part A) 30°C (86°F)	C/A (Part B) 44°C (111°F)	Mixed 33°C (91°F)
Product Weight	1.7-1.8 kg/l (14.2-15.0 lb/gal)		
VOC	130 g/l	UK - PG6/23(92), Appendix 3	
	1.36 lb/gal (163 g/l)	USA - EPA Method 24	

Interzone 954

Modified Epoxy

Surface Preparation

The performance of this product will depend upon the degree of surface preparation. The surface to be coated must be clean and free from contamination. Prior to paint application all surfaces should be assessed and treated in accordance with ISO 8504:1992.

Accumulated dirt and soluble salts must be removed. Dry bristle brushing will normally be adequate for accumulated dirt. Soluble salts should be removed by fresh water washing.

Oil or grease should be removed in accordance with SSPC-SP1 solvent cleaning.

Abrasive Blast Cleaning

Abrasive blast clean to Sa2 (ISO 8501-1:1988) or SSPC-SP6. If oxidation has occurred between blasting and application of Interzone 954, the surface should be reblasted to the specified visual standard.

Surface defects revealed by the blast cleaning process, should be ground, filled, or treated in the appropriate manner.

A surface profile of 50-75 microns (2-3 mils) is recommended.

Ultra High Pressure Hydroblasting/Abrasive Wet Blasting

May be applied to surfaces prepared to Sa2 (ISO 8501-1:1988) or SSPC-SP6 which have flash rusted to no worse than Grade HB2½M (refer to International Hydroblasting Standards). It is also possible to apply to damp surfaces in some circumstances. Further information is available from International Protective Coatings.

Aged Coatings

Interzone 954 is suitable for overcoating some sound intact aged coatings. To ensure compatibility, application and evaluation of a test patch is required.

Application

Mixing	Material is supplied in two containers as a unit. Always mix a complete unit in the proportions supplied. Once the unit has been mixed it must be used within the working pot life specified.			
	(1) Agitate Base (Part A) with a power agitator.			
	(2) Combine entire contents of Curing Agent (Part B) with Base (Part A) and mix thoroughly with power agitator.			
Mix Ratio	4 parts : 1 part by volume			
Working Pot Life	10°C (50°F) 3 hours	15°C (59°F) 2 hours	25°C (77°F) 90 minutes	40°C (104°F) 45 minutes
Airless Spray	Recommended.	- Tip range 0.53-0.66 mm (21-26 thou) - Total output fluid pressure at spray tip not less than 176 kg/cm ² (2,500 p.s.i.)		
Air Spray (Pressure Pot)	Recommended.	Gun	DeVilbiss MBC or JGA	
		Air Cap	62	
		Fluid Tip	AC	
Brush	Suitable	Typically 100-150 microns (4-6 mils) can be achieved		
Roller	Suitable	Typically 75-125 microns (3-5 mils) can be achieved		
Thinner	International GTA220 (or GTA415)	Do not thin more than allowed by local environmental legislation.		
Cleaner	International GTA822 (or GTA415)			
Work Stoppages	Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with International GTA822. Once units of paint have been mixed they should not be resealed and it is advised that after prolonged stoppages work recommences with freshly mixed units.			
Clean Up	Clean all equipment immediately after use with International GTA822. It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, including any delays. All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.			

Interzone 954

Modified Epoxy

Product Characteristics

Maximum film build in one coat is best attained by airless spray. When applying by methods other than airless spray, the required film build is unlikely to be achieved.

Application by air spray may require a multiple cross spray pattern to attain maximum film build. Low or high temperatures may require specific application techniques to achieve maximum film build.

When applying Interzone 954 by brush or roller, it may be necessary to apply multiple coats to achieve the total specified system dry film thickness.

Surface temperature must always be a minimum of 3°C (5°F) above dew point.

Do not apply at steel temperatures below 5°C (41°F).

When applying Interzone 954 in confined spaces ensure adequate ventilation.

In special cases where overcoating is required and curing has been at low temperatures and high relative humidities ensure no amine bloom is present prior to application of subsequent topcoats.

Condensation occurring during or immediately after application may result in a matt finish and an inferior film.

Premature exposure to ponding water will cause a colour change, especially in dark colours.

In common with all epoxies Interzone 954 will chalk and discolour on exterior exposure. However, these phenomena are not detrimental to anti-corrosive performance.

Where a durable cosmetic finish with good gloss and colour retention is required overcoat with recommended topcoats.

When applied between tides on jetties, piling etc., Interzone 954 can be immersed within 30 minutes. This will lead to whitening of dark colours but will not affect ultimate anti-corrosive performance.

For use in atmospheric service a minimum dry film thickness of 350 microns (14 mils) is required in one coat when applied direct to steel, for water immersion a minimum of 500 microns (20 mils) dry film thickness is recommended. In each case protection can be achieved in a single coat application by airless spray.

Interzone 954 can be used as a non-skid deck system by modification with addition of GMA132 (crushed flint) aggregate. Application should then be to a suitably primed surface. Typical thicknesses will be between 500-1,000 microns (20-40 mils). Preferred application is by a suitable large tip hopper gun (e.g. Sagola 429 or Air texture gun fitted with a 5-10 mm nozzle). Trowel or roller can be used for small areas. Alternatively, a broadcast method of application can be used. Consult International Protective Coatings for further details.

Compatible with sacrificial and impressed current cathodic protection systems.

Systems Compatibility

Interzone 954 will generally be applied to bare steel prepared by dry abrasive blasting, wet abrasive blasting or ultra high pressure hydroblasting.

The following primers are recommended for Interzone 954:

Intercure 200	Interzinc 42
Intergard 251	Interzinc 52
Intergard 269 (for underwater use)	Interzinc 315
Interline 982 (for underwater use)	Interzone 1000
Interzinc 12 (mist or tie coat recommended)*	
Interzinc 22 (mist or tie coat recommended)*	

The following topcoats are recommended for Interzone 954:

Interfine 629 HS
Intergard 740
Intersleek 167
Interthane 990

For other suitable primers/topcoats, consult International Protective Coatings.

* See relevant product data sheet for details.

Interzone 954

Modified Epoxy

Additional Information

Further information regarding industry standards, terms and abbreviations used in this data sheet can be found in the following sections of the International Protective Coatings data manual:

- Definitions & Abbreviations
- Surface Preparation
- Paint Application
- Theoretical & Practical Coverage

Individual copies of these information sections are available upon request.

Safety Precautions

This product is intended for use only by professional applicators in industrial situations in accordance with the advice given on this sheet, the Material Safety Data Sheet and the container(s), and should not be used without reference to the Material Safety Data Sheet (MSDS) which International Protective Coatings has provided to its customers.

All work involving the application and use of this product should be performed in compliance with all relevant national, Health, Safety & Environmental standards and regulations.

In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation.

If in doubt regarding the suitability of use of this product, consult International Protective Coatings for further advice.

Pack Size	20 litre unit	Interzone 954 Base	16 litres in a 20 litre container
		Interzone 954 Curing Agent	4 litres in a 5 litre container
	5 gallon unit	Interzone 954 Base	4 gallons in 5 gallon container
		Interzone 954 Curing Agent	1 gallon in a 1 gallon container
For availability of other pack sizes contact International Protective Coatings			
Shipping Weight	U.N. Shipping No. 1263		
	20 litre unit	30.4 kg (67 lb) Base (Part A)	4.6 kg (10.1 lb) Curing Agent (Part B)
	5 gallon unit	25.6 kg (56.6 lb) Base (Part A)	5.2 kg (11.4 lb) Curing Agent (Part B)
Storage	Shelf Life	12 months minimum at 25°C (77°F). Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.	

Disclaimer

The information given in this sheet is not intended to be exhaustive and any person using the product for any purpose other than that specifically recommended in this sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. Any warranty, if given, or specific Terms & Conditions of Sale are contained in International's Terms & Conditions of Sale, a copy of which can be obtained on request. Whilst we endeavour to ensure that all advice we give about the product (whether in this sheet or otherwise) is correct we have no control over either the quality or condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability whatsoever or howsoever arising for the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of the use of the product. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.

It is the user's responsibility to check that this sheet is current prior to using the product. Issue date: 1st June 1997

Copyright © International Paint Ltd. * and International are trademarks.

International Protective Coatings

Worldwide Availability

World Centre	Asia Region	Australasia Region	Europe Region	Middle East Region	North America Region	South America Region
50 George Street London W1A 2BB England	3 Neythal Road Jurong Town Singapore 628570	115 Hyde Road Yeronga Brisbane Queensland Australia	50 George Street London W1A 2BB England	PO Box 37 Dammam 31411 Saudi Arabia	6001 Antoine Drive Houston Texas 77091	Rua Gomes de Carvalho, 1356, 15° Andar, Vila Olímpia, São Paulo, S.P. CEP: 04547-005 Brazil
Tel: (44) 171 612 1400 Fax: (44) 171 612 1561	Tel: (65) 663 3066 Fax: (65) 266 5287	Tel: (61) 7 3892 8866 Fax: (61) 7 3892 4287 H&S (61) 1800 807 001	Tel: (44) 171 612 1410 Fax: (44) 171 612 1555	Tel: (966) 3 842 8436 Fax: (966) 3 842 4361	Tel: (1) 713 682 1711 Fax: (1) 713 684 1327	Tel: (011) 3044 0344 Fax: (011) 3044 0322